

IN THE SPECIFICATION

Please amend the table at page 32 as shown on the following page.

Application No. 10/590,932
 Reply to Office Action of September 3, 2009

Fractions [% by weight]								
Ex.	PMMA [%]	PVDF [%]	Film thickness [μm]	Elastomer particle content of the PMMA fraction [%]	Elongation at break without thermal stress [%]	Elongation at break after 10 days at 60°C [%]	Ratio of after/without thermal stress [%]	
A	30	70	500	65	262	177	68	
A-Comp.	30	70	500	0	293	14	5	
B	30	70	250	65	299	292	98	
B-Comp.	30	70	250	0	442	7	2	
C-Comp.	30	70	50	65	355	305	86	
D-Comp.	30	70	50	0	393	321	82	
E	40	60	200	60	273	205	75	
F	40	60	200	40	357	292	82	
G-Comp.	40	60	200	20	331	9	3	

Comp. = comparative example
 “PMMA” means standard PMMA or impact-modified PMMA